

Characteristics	Test Method	Unit of Measurement	(Range of Values)
Density	ASTM C97	g/cm <sup>3</sup> LBS/FT <sup>3</sup>	2.3 – 2.4 g/cm <sup>3</sup>
Flexural Strength (Modules Rupture)	ASTM C880	MPa	100-140 (Dry) 120-156 (Wet)
Water Absorption	ASTM C97	%	0.03
Compressive Strength	ASTM C170	MPa	143-150 (Dry) 126-146 (Wet)
Coefficient of Thermal Expansion	ASTM C531	Inch/°F	2.3x10 <sup>-5</sup>
Barcol Hardness	ASTM D2583	Index (0-100)	87
Abrasion Resistance	ASTM C501	Wear Index	95 Minimum
Gloss	Gloss Meter	% Incident light reflected at 60°	45% Minimum
Breaking Strength	ASTM C648	LBF	4160
Impact Resistance	ASTM D256	J/M	40 - 61
Stain Resistance	ANSI Z124	Pass/Fail	Pass
Wear & Cleanability	ANSI Z124	Pass/Fail	Pass
Boiling Water Resistance	NEMA LD 3-3.5		No Effect
Color Fastness	ANSI Z124	Pass/Fail	Pass
Moderate Chemical Resistance	ANSI Z124	Pass/Fail	Pass
Surface Roughness	ISO 4287	μM	0.38-0.47